

Dead Burned Magnesite - DBM

Typical chemical values

| Product | MgO (%) | SiO ₂ (%) | CaO (%) | Al ₂ O ₃ (%) | Fe ₂ O ₃ (%) | Loss on ignition(%) | Particle size |
|------------------------------------|---------|----------------------|---------|------------------------------------|------------------------------------|---------------------|----------------------------|
| Dead burned magnesite 9003 | 90,00 | 4,50 | 2,50 | 1,50 | 1,50 | 1,00 | 0 - 3 mm (< 1 mm: 55,00%) |
| Dead burned magnesite 9010 | 90,00 | 4,50 | 2,50 | 1,50 | 1,50 | 0,60 | 0 - 10 mm (< 1 mm: 10,00%) |
| Magnesium oxide TA-3 | 91,50 | 3,2 | 1,85 | 1,00 | 1,25 | 0,95 | 60,00% < 63 µm/ 250 mesh |
| Magnesium oxide TA-6 | 89,50 | 7,00 | 3,50 | 0,50 | 0,50 | 0,50 | 60,00% < 63 µm/ 250 mesh |
| Dead burned magnesite Extra | 96,50 | 1,00 | 2,00 | 0,10 | 0,60 | 0,20 | 0 - 15 mm (< 1 mm: 10,00%) |