

Magnesium carbonate - MC

Typical chemical values

| Product | MgO (%) | SiO ₂ (%) | CaO (%) | Al ₂ O ₃ (%) | Fe ₂ O ₃ (%) | Loss on ignition (%) | Particle size |
|-------------------------------|---------|----------------------|---------|------------------------------------|------------------------------------|----------------------|---------------------------|
| Magcarluv MC 45 | 45,00 | 4,50 | 3,00 | 0,20 | 0,40 | 51,00 | 99,50% < 40 µm/ 360 mesh |
| Magcarluv MC extra 45 | 45,50 | 3,00 | 0,90 | 0,05 | 0,05 | 48,80 | 99,50% < 40 µm/ 360 mesh |
| Magcarluv MC extra 100 | 45,50 | 3,00 | 0,90 | 0,05 | 0,05 | 48,80 | 99,50% < 100 µm/ 150 mesh |