

## Magnesium carbonate - MC

### Typical chemical values

| Product                       | MgO (%) | SiO <sub>2</sub> (%) | CaO (%) | Al <sub>2</sub> O <sub>3</sub> (%) | Fe <sub>2</sub> O <sub>3</sub> (%) | Loss on ignition (%) | Particle size             |
|-------------------------------|---------|----------------------|---------|------------------------------------|------------------------------------|----------------------|---------------------------|
| <b>Magcarluv MC 45</b>        | 45,00   | 4,50                 | 3,00    | 0,20                               | 0,40                               | 51,00                | 99,50% < 40 µm/ 360 mesh  |
| <b>Magcarluv MC extra 45</b>  | 45,50   | 3,00                 | 0,90    | 0,05                               | 0,05                               | 48,80                | 99,50% < 40 µm/ 360 mesh  |
| <b>Magcarluv MC extra 100</b> | 45,50   | 3,00                 | 0,90    | 0,05                               | 0,05                               | 48,80                | 99,50% < 100 µm/ 150 mesh |