

<b>Products</b>	<b>Average Partice size [mm]</b>	<b>Coating</b>	<b>Effective Density [g/cm<sup>3</sup>]</b>	<b>Temperature resistance [°C]</b>	<b>Characteristic</b>
<b>MFL-81GTA</b>	10 - 30	Talc	0.20 - 0.26	130 - 140	Very fine surface
<b>MFL-81CGA</b>	10 - 30	Calcium carbonate	0.20 - 0.26	130 - 140	Very fine surface
<b>MFL-SEVEN</b>	20 - 40	Calcium carbonate	0.11 - 0.17	130 - 140	Very fine surface
<b>MFL-HD30CA</b>	20 - 40	Calcium carbonate	0.11 - 0.17	140 - 150	High pressure
<b>MFL-HD60CA</b>	50 - 70	Calcium carbonate	0.10 - 0.14	140 - 150	High pressure
<b>MFL-100MCA</b>	60 - 70	Calcium carbonate	0.10 - 0.14	150 - 160	High pressure
<b>MFL-110CAL</b>	90 - 120	Calcium carbonate	0.06 - 0.10	160 - 170	Ultra light
<b>MFL-UPR60</b>	50 - 75	Calcium carbonate	0.10 - 0.14	140 - 150	High pressure

The values given are typical values and therefore do not represent a specification.